

Table of standard equivalent

Maizeme No.	ALMANYA Kalite	ALMANYA DIN Standartı	AMERIK A Kalite	AMERIK A ASTM Standartı	INGiltere Kalite	INGiltere BS Standartı	FRANSA Kalite	FRANSA NF Standartı
1,0254	St.37,0	DIN 1629	Gr. A	A 53	S 360	3601	TU E 220 A	A 49-112
1,0256	St.44,0	DIN 1629	Gr. B	A 53	S 430	3601	TU E 235 A	A 49-112
1,0421	St.52,0	DIN 1629	Gr. 3	A 252	50 B	4360	TU 52-b	A 49-311
1,0581	St.52,4	-		A 252	HFS 5	6323		A 49-212
1,0305	St.35,8	DIN 17175	Gr. FPA	A 369	S 320	3059/1	TU 37-c	A 49-213
		DIN 17175	Gr. A	A 53+A 106	HFS 360	3602/1		A 49-215
		DIN 17175		A 179	CFS 360	3602/1		A 49-212
		DIN 17175		A 192	360	3059/2		A 49-213
1,0405	St.45,8	DIN 17175	Gr. B	A 106	HFS 430	3602/1	TU 42-c	A 49-215
		DIN 17175	Gr. A-1	A 210	CFS 430	3602/1		A 49-213
		DIN 17175	Gr. FPA	A 369	440	3059/2		A 49-215
1,0481	17 Mn 4	DIN 17175	Gr. C	A 106	440	3059/2	TU 48-c	A 49-213
		DIN 17175	Gr. C	A 210	(430)	3602/1		A 49-215
1,0482	19 Mn 5	DIN 17175	-	-			TU 52-c	A 49-213
-	-	-	-	-	500 Nb	3602/1	-	-
1,5415	15 Mo 3	DIN 17175	-	-	243	3059/2	TU 15 D 3	A 49-213
		DIN 17175	-	-		3606		A 49-215
1,5423	16 Mo 5	VdTUV-Wbl.201	Gr. T1	A 161+A 209	245	3606	-	-
		VdTUV-Wbl.201	Gr. P 1/FP 1	A 335+A 369		3606	-	-
-	-	-	Gr. P2	A 335	-		TU 15 CD 2-05	A 49-213
-	-	-	Gr. FP2	A 369	-			A 49-215

1,7335	13 CrMo 4 4	DIN 17175	Gr. T 12	A 213	620-440	3606	TU 13 CD 4-04	A 49- 213
		DIN 17175	Gr. P 12	A 335	620-460	3606		A 49- 213
		DIN 17175	Gr. FP 12	A 369	620	3606		A 49- 213
		DIN 17175		A 369		3059/2		A 49- 213
1,7380	10 CrMo 9 10	DIN 17175	Gr. T 22	A 199+A 200	622-440	3059/2	TU 10 CD 9-10	A 49- 213
		DIN 17175	Gr. T 22	A 213	622-490	3059/2		A 49- 213
	10	DIN 17175	Gr. P 22/FP 22	A 335+A 369	622	3604/3606		A 49- 215